

**PTFE-GLASS FABRIC**

Series No.	Standard Widths mm	Nominal Thickness $\mu$	Weight G/M <sup>2</sup>	PTFE Content %	Tensiles N/5cm	Dielectric Volts
------------	--------------------	-------------------------	-------------------------	----------------	----------------	------------------

**ELECTRICAL GRADE - PTFE GLASS**

7030	1000	80	160	69	800	2800
7060	1000	150	320	67	1200	4000

**PREMIUM GRADE - PTFE GLASS**

7039	1000	75	145	66	800	2500
7069	1000	145	309	65	1200	3800
7109	1000	250	534	62	2300	4000
7109	2000	250	534	62	2300	4000
7119	1000	275	600	66	2300	4600
7119	2000	275	600	66	2300	4600

**STANDARD GRADE - PTFE GLASS**

7058	1000	125	255	58	1200	2500
7058	1500	125	255	58	1200	2500
7068	1000	140	296	63	1200	3600
7068	1500	140	296	63	1200	3600
7108	1000	230	490	59	2300	3500
7108	1500	230	490	59	2300	3500
7108	2400	230	490	59	2300	3500
7148	1000	330	680	57	3300	2800
7148	1500	330	680	57	3300	2800
7148	2400	330	680	57	3300	2800
7278	2600	700	1085	43	4200	2800
7278MG	2600	820	1085	46	4500	2500

**CREASE & TEAR RESISTANT - PTFE GLASS**

7064	1000	140	296	63	1200	2000
7104	1000	230	490	59	1500	2200

**ANTI-STATIC BLACK - PTFE GLASS**

7033AS	1000	75	146	66	800	---
7053AS	1000	125	255	58	1200	---
7053AS	1000	125	255	58	1200	---
7103AS	1000	230	490	59	2300	---
7103AS	1500	230	490	59	2300	---
7103AS	2400	230	490	59	2300	---
7143AS	1000	330	680	57	3300	---
7143AS	1500	330	680	57	3300	---
7143AS	2400	330	680	57	3300	---
7273AS	2600	700	1085	43	4200	---

**INDUSTRIAL GRADE - PTFE GLASS**

5038	1000	70	135	64	800	1500
5038	1500	70	135	64	800	1500
5058	1000	115	240	54	1200	2000
5058	1500	115	240	54	1200	2000
5068	1000	127	272	60	1200	3000
5108	1000	220	455	55	2300	3200
5108	1500	220	455	55	2300	3200

**MECHANICAL GRADE - PTFE GLASS**

5037	1000	68	120	59	800	1000
5057	1000	110	220	48	1200	1200
5147	1000	270	527	45	3300	2000

**ANTI-STATIC BLACK - PTFE GLASS - SINGLES SERIES**

5053AS	1000	115	240	54	1200	---
5063AS	1000	127	272	60	1200	---

Note: Nominal thickness, tensile strength and dielectric values are typical and are not intended as a specification minimum.  
Weight g/m<sup>2</sup>  $\pm$  5% process variation.  
PTFE content  $\pm$  2% process variation.

**TACONIC U.S. OPERATIONS**

Taconic  
Industrial Products Division  
East Coast Office  
136 Coonbrook Rd, PO Box 69  
Petersburgh, NY 12138

Tel: +(1)-518-658-3202 / 800-982-26642  
Fax: +(1)-518-658-3186 / 800-757-6245  
Email: info@4taconic.com

Taconic  
Industrial Products Division  
West Coast Office  
3070 Skyway Drive - Bldg. 203  
Santa Maria, CA 93455

Tel: +(1)-805-925-8070 / 800-832-0982  
Fax: +(1)-805-925-7484 / 800-400-2220  
Email: info@4taconic.com

**TACONIC EUROPEAN OPERATIONS**

Taconic International Ltd.  
Industrial Products Division  
Mullingar Business Park  
Mullingar, County Westmeath  
Republic of Ireland

Tel: +(353)-44-40477  
Fax: +(353)-44-42514  
Email: ipd@4taconic.com

Taconic France  
ZA des Vernays  
74210 Doussard, France  
Tel: +(33)-450-443147  
Fax: +(33)-450-448845  
Email: dft@4taconic.com

Taconic United Kingdom  
15 Brunell Close  
Drayton Field Industrial Estate  
Daventry, Northants NN11 5RB  
England

Tel: +(44)-13-2730 4500  
Fax: +(44)-13-2730 4501  
Email: uk\_sales@4taconic.com

**TACONIC ASIAN OPERATIONS**

Korea Taconic Company Ltd.  
Industrial Products Division  
906-2 Na-dong APT Factory  
148 Yatap-dong Bundang-ku  
Sungnam-si Kyungki-do, Korea

Tel: +(82)-342-704 1858  
Fax: +(82)-342-704 1857  
Email: ktc@4taconic.com